

Decorative body Light - P1

Chemical analysis	SiO ₂	72,8 %
	Al ₂ O ₃	20,8 %
	TiO ₂	1,5 %
	Fe ₂ O ₃	1,4 %
	CaO	0,0 %
	MgO	0,2 %
	K ₂ O	2,3 %
	Na ₂ O	0,3 %
	Loss on ignition	6,1 %

Firing behaviour	°C
Firing temperature	1040
Dry shrinkage	
Firing shrinkage	
Total shrinkage	
Water absorption	15,4
Firing color	cream
L*	75
a*	5,5
b*	13,2

Screen analysis	< 125 µm	98,0 %
------------------------	----------	--------

Pasticity acc. to Pfefferkorn	21 mm
--------------------------------------	-------

Above technical data are for information only. Our materials are sold according to samples and according to our general selling terms.