

## Decorative body Salmon - L1

---

<b>Chemical analysis</b>	SiO <sub>2</sub>	62,8 %
	Al <sub>2</sub> O <sub>3</sub>	20,6 %
	TiO <sub>2</sub>	0,9 %
	Fe <sub>2</sub> O <sub>3</sub>	2,6 %
	CaO	9,8 %
	MgO	0,5 %
	K <sub>2</sub> O	2,5 %
	Na <sub>2</sub> O	0,3 %
	Loss on ignition	9,2 %

---

<b>Firing behaviour</b>	°C
Firing temperature	1050
Total shrinkage	6,6
Water absorption	9,7
Firing color	salmon
L*	67
a*	12,0
b*	18,1

---

<b>Screen analysis</b>	< 125 µm	98,0 %
------------------------	----------	--------

---

<b>Plasticity acc. to Pfefferkorn</b>	21 mm
---------------------------------------	-------

---

Above technical data are for information only. Our materials are sold according to samples and according to our general selling terms.