

Decorative body Salmon - S1

Chemical analysis	SiO ₂	62,8 %
	Al ₂ O ₃	20,6 %
	TiO ₂	0,9 %
	Fe ₂ O ₃	2,6 %
	CaO	9,8 %
	MgO	0,5 %
	K ₂ O	2,5 %
	Na ₂ O	0,3 %
	Loss on ignition	9,2 %

Firing behaviour	°C
Firing temperature	1050
Total shrinkage	6,6
Water absorption	9,7
Firing color	salmon
L*	67
a*	12,0
b*	18,1

Screen analysis	< 125 µm	98,0 %
------------------------	----------	--------

Plasticity acc. to Pfefferkorn	21 mm
---------------------------------------	-------

Above technical data are for information only. Our materials are sold according to samples and according to our general selling terms.