

## Powdered clay - T901

---

<b>Chemical analysis</b>	SiO <sub>2</sub>	65-75 %
	Al <sub>2</sub> O <sub>3</sub>	18-24 %
	TiO <sub>2</sub>	0,8-1,5 %
	Fe <sub>2</sub> O <sub>3</sub>	1,0-5,0 %
	CaO	0,1-0,4 %

---

<b>Mineral analysis</b>	Kaolinite	25-35 %
	Mica	15-25 %
	Quartz	35-50 %
	Feldspar	1-6 %
	Fe-Ti	1-5 %

---

<b>Sedimentation analysis</b>	< 250 µm	100,0 %
	< 63 µm	95,0 %
	< 20 µm	80,0 %
	< 2 µm	50,0 %

---

### Further data

Moisture	max. 1 %
Bulk weight	500-650 g/l
Color	white-beige-greyish

---